

TECHNICAL CHARACTERISTICS: CEPPO

ANEXO G: GRUPO B1a

UNE- EN 14411: 2016 Anexo / Annex G

ISO 13006: 2018 Anexo / Annex G

TEST DESCRIPTION	STANDARD	TEST VALUE
Dimensions + Surface quality.	UNE-EN ISO 10545- 2	Complies
Water Absortion.	UNE-EN ISO 10545- 3	≤0,5%
Modulus of rupture.	UNE- EN ISO 10545-4	2 35 N/ mm 2
Breaking Strength.	UNE. EN ISO 10545-4	21300 N
Resistance to thermal Shock.	UNE- EN ISO 10545-9	Resistente / Resistant
Crazing resistance.	UNE- EN ISO 10545-12	Resistente / Resistant
Frost resistance.	UNE- EN ISO 10545-12	Resistente / Resistant
Slip Resistance	>0.42 ANSI A137.1:2017.9.76	Dynamic coefficient of friction DCOF
Chemical resistance: High concentration of acids and alkalis.	UNE- EN ISO 10545-13	Minimun class B
Chemical resistance: Low concentration of acids and alkalis.	UNE- EN ISO 10545-13	Minimun class LB
Chemical resistance: Household chemicals and swimming pool salts.	UNE- EN ISO 10545-13	Minimun class LB
Stain resistance.	UNE- EN ISO 10545- 14	Minimun Class 3

PACKING AND WEIGHT

Size (cm)	Pzas /Cj	m2/Cj	Kg/Cj	Kg/m2	Pzs/Epl	Cjas/Epl	m2/Epl	Kg/Epl
60x120 (59,5x120) Rect.	2	1,428	28,75	20,13	80	40	57,12	1.170,00
100x100 (99,5x99,5) Rect.	2	1,980	44,16	22,31	48	24	47,52	1.080,00
60x60 (59,5x59,5) Rect.	4	1,41	28,47	20,11	144	36	50,98	1.045,00